

Application No. 10/716,190  
Filed: November 18, 2003  
TC Art Unit: 1732  
Confirmation No.: 4133

TO THE CLAIMS

Please ~~amend~~ claim 1 and add claims 4-10 as shown in the Summary of the Claims section, *infra*. No new matter has been added. Additions are underlined and deletions are struckthrough.

Application No. 10/716,190

Filed: November 18, 2003

TC Art Unit: 1732

Confirmation No.: 4133

SUMMARY OF THE CLAIMS

Claim 1 (Currently amended). A method for controlling a thickness of a skin layer on a composite product having the skin layer and a core layer, comprising steps of:

- (a) adding a carbon nanomaterial to either a first thermoplastic resin or a second thermoplastic resin to cause or increase a difference in viscosity between those resins; and
- (b) injection molding both said resins into a mold ~~together~~ ~~or separately~~ to produce said composite product having the skin layer containing said first thermoplastic resin and the core layer containing said second thermoplastic resin so as to control the thickness of the skin layer by said difference in viscosity,

wherein said first thermoplastic resin is firstly injected into the mold, then said second thermoplastic resin is injected into said first thermoplastic resin in the mold.

Claim 2 (Original). The method according to Claim 1, wherein said first resin and said second resin are same kind of resin.

Claim 3 (Original). The method according to Claim 1, wherein said first resin and said second resin are different kinds of resins.

Claim 4 (New). The method according to Claim 1, wherein adding the carbon nanomaterial to the first thermoplastic resin or the second thermoplastic includes kneading said carbon nanomaterial and thermoplastic resin to provide better dispersion efficiency.

Application No. 10/716,190

Filed: November 18, 2003

TC Art Unit: 1732

Confirmation No.: 4133

Claim 5 (New). The method according to Claim 1, wherein adding the carbon nanomaterial to the thermoplastic resins comprises adding the carbon nanomaterial in a range between about 1 and about 20 percent by mass.

Claim 6 (New). The method according to Claim 1, wherein adding the carbon nanomaterial comprises adding fullerene or carbon nanotube to a polypropylene resin to decrease the viscosity of the polypropylene resin.

Claim 7 (New). The method according to Claim 6, wherein the carbon nanotube has a particle length and a viscosity variation is controlled by controlling the particle length of the carbon nanotube.

Claim 8 (New). The method according to Claim 7, wherein the viscosity increases with increasing particle length of the carbon nanotube.

Claim 9 (New). The method according to Claim 1, wherein carbon nanomaterial is added to the second thermoplastic resin so that the viscosity of the second thermoplastic resin is made greater than the viscosity of the first thermoplastic resin and the skin layer of the first thermoplastic resin is pressed and stretched by the more viscous second thermoplastic layer to control its thickness.

Claim 10 (New). The method according to Claim 1, wherein carbon nanomaterial is added to the first thermoplastic resin so that the viscosity of the first thermoplastic resin is made less than

-4-

WEINGARTEN, SCHURGIN,  
GARNSDIN & LEBOVICI LLP  
TEL.: (617) 542-2290  
FAX: (617) 451-0313

# BEST AVAILABLE COPY

02/17/2006 15:04 FAX 16174510313

WSGL

0007

Application No. 10/716,190

Filed: November 18, 2003

TC Art Unit: 1732

Confirmation No.: 4133

the viscosity of the second thermoplastic resin and the skin layer of the first thermoplastic resin is pressed and stretched by the more viscous second thermoplastic layer to control its thickness.

-5-

WEINGARTEN, SCHURGIN,  
GACNEBIN & LEBOVICI LLP  
TEL. (617) 542-2290  
FAX. (617) 451-0313